

Product Texts

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 127UV is a UV-stabilized high viscosity acetal homopolymer developed for applications in automotive interiors. It represents a dramatic improvement over Delrin® 107 in mechanical performance after prolonged UV exposure and thermal stability.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	1.9	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.9	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	1	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	1.05	kg	-
Mold Shrinkage, MD	0.0195	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0195	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3000	MPa	ISO 527
^[C] Yield stress	70	MPa	ISO 527
^[C] Yield strain	23	%	ISO 527
^[C] Nominal strain at break	45	%	ISO 527
^[C] Charpy impact strength, +23°C	400	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	350	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	2910	MPa	ASTM D 638
Tensile Strength	67	MPa	ASTM D 638
Tensile Strength at Yield	67	MPa	ASTM D 638
Elongation at Yield	26	%	ASTM D 638
Elongation at Break	75	%	ASTM D 638
Flexural Modulus	2800	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	120	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	160	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.84	mm	-

Delrin® 127UV NC010

POM

Delrin

Coefficient of Thermal Expansion, MD	120	E-6/K	ASTM D 696
DTUL @ 66 psi	167	°C	ASTM D 648
DTUL @ 264 psi	107	°C	ASTM D 648
Melting Temperature	178	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.5	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.4	-	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	60	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
^[C] Comparative tracking index	600	-	IEC 60112
ASTM Data			
Dielectric Constant, 1 MHz	3.3	-	ASTM D 150
Surface Resistivity	1E15	Ohm	ASTM D 257
Volume Resistivity	1E14	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	1.2	%	Sim. to ISO 62
^[C] Humidity absorption	0.3	%	Sim. to ISO 62
^[C] Density	1420	kg/m ³	ISO 1183
Density	1420	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Film Extrusion, Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Wire/Cable Extrusion, Other Extrusion

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Special Characteristics

High impact or impact modified, Light stabilized or stable to light, U.V. stabilized or stable to weather

Features

Creep Resistance, Fatigue Resistance, Thermal Stability, Weldable, Homopolymer

Applications

Automotive

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.