

Product Texts

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 900P is a general purpose low viscosity acetal homopolymer for multicavity and thin wall molding with improved processing thermal stability and low VOC emissions.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	21	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.9	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	1.05	kg	-
Mold Shrinkage, MD	0.0175	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0185	mm/mm	ASTM D 955

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3200	MPa	ISO 527
^[C] Yield stress	71	MPa	ISO 527
^[C] Yield strain	12	%	ISO 527
^[C] Nominal strain at break	23	%	ISO 527
^[C] Tensile creep modulus, 1h	2800	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	1500	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	7.5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6.5	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	3480	MPa	ASTM D 638
Tensile Strength at Yield	69	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	3240	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	94	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	162	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	160	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

Delrin® 900P NC010

POM

Delrin

^[C] Oxygen index	23	%	ISO 4589-1/-2
-----------------------------	-----------	---	---------------

ASTM Data

UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	163	°C	ASTM D 648
DTUL @ 264 psi	105	°C	ASTM D 648
Melting Temperature	178	°C	ASTM D 3418

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
-----------------------	-------	------	---------------

ISO Data

^[C] Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.8	-	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	50	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600	-	IEC 60112

ASTM Data

Dielectric Strength, Short Time	17.3	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.006	-	ASTM D 150
Dielectric Constant, 1 MHz	3.6	-	ASTM D 150
Surface Resistivity	5E14	Ohm	ASTM D 257
Volume Resistivity	2E14	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
------------------	-------	------	---------------

^[C] Water absorption	1.4	%	Sim. to ISO 62
^[C] Humidity absorption	0.4	%	Sim. to ISO 62
^[C] Density	1420	kg/m ³	ISO 1183
Water Absorption, 24hr	0.43	%	ASTM D 570
Water Absorption, Equilibrium	1.4	%	ASTM D 570
Density	1420	kg/m ³	ASTM D 792

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Features

Creep Resistance, Fatigue Resistance, Low Emission, Thermal Stability, Weldable, Homopolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.