

**PC-ABS 5356**

(PC+ABS)

MBA Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	30	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	49	MPa	ISO 527
Flexural modulus, 23°C	2350	MPa	ISO 178
Izod notched impact strength, +23°C	18	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1130	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 250	°C	-
Mold temperature	90 - 105	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	240 - 250	°C	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Special Characteristics**

High impact or impact modified

**Features**

Copolymer

**Certifications**

Recycled Resin Content

**Applications**

Automotive

**Regional Availability**

North America, Europe, Asia Pacific