

Product Texts

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® RAFG500P is a general purpose medium viscosity acetal homopolymer for injection molding, with reduced lifecycle greenhouse gas emissions and lower fossil resource use. Delrin® RAFG500P has improved processing thermal stability and a good combination of mechanical properties. It has been developed for applications in contact with food.

Delrin® Renewable Attributed base polymer is produced from 100% bio-feedstock from waste*. 100% certified renewable electricity is used for its production.

This approach helps customers in achieving their sustainability goals.

* according to ISCC Plus mass balance certification.

FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from your DuPont representative.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	13	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3100	MPa	ISO 527
^[C] Yield stress	71	MPa	ISO 527
^[C] Yield strain	17	%	ISO 527
^[C] Nominal strain at break	30	%	ISO 527
^[C] Tensile creep modulus, 1h	2800	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	1600	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	300	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	280	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	94	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	158	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	155	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Delrin® RAFG500P NC010

POM

Delrin

Other properties	Value	Unit	Test Standard
^[C] Water absorption	1.4	%	Sim. to ISO 62
^[C] Humidity absorption	0.4	%	Sim. to ISO 62
^[C] Density	1420	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Features

Thermal Stability, Homopolymer

Certifications

Food contact, ISCC Plus

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or
- When packaging stays open for a significant time.