

**Denistat M 00U 03 SC1**

POM

VAMP TECH SPA

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Izod impact strength, +23°C	<b>40</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	<b>2100</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>45</b>	MPa	ASTM D 638
Elongation at Break	<b>8</b>	%	ASTM D 638
<b>Thermal properties</b>			
<b>ASTM Data</b>			
Vicat Temperature	<b>150</b>	°C	ASTM D 1525
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	<b>1000</b>	Ohm	ASTM D 257
<b>Other properties</b>			
Density	<b>1420</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>70</b>	°C	-
Pre-drying - Time	<b>3</b>	h	-
Melt temperature	<b>190</b>	°C	-
Mold temperature	<b>90</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Special Characteristics**

Increased electrical conductivity, Anti-static, Flame retardant

**Regional Availability**

Europe