

PC/ABS Alloy 380 Grey

(PC+ABS)

Shuman Plastics, Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	48.3	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Izod Impact notched, 1/8 in	480	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

North America, Europe, Asia Pacific

Chemical Resistance

General Chemical Resistance