

Edgetek™ AT-000/000 BK022

POM

Avient Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.019	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	64	MPa	ASTM D 638
Flexural Modulus	2700	MPa	ASTM D 790
Flexural Strength	85	MPa	ASTM D 790
Izod Impact notched, 1/8 in	150	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 264 psi	105	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	1E15	Ohm	ASTM D 257
Other properties			
Density	1400	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	2 - 3	h	-
Mold temperature	75 - 85	°C	-
Zone 1	190 - 200	°C	-
Zone 2	190 - 200	°C	-
Zone 3	190 - 200	°C	-

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Delivery form

Black

Regional Availability

Asia Pacific

Additives

Lubricants