

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	23	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2500	MPa	ISO 527
Stress at break	56	MPa	ISO 527
Strain at break	9	%	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Charpy impact strength, +23°C	75	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1400	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets

**Regional Availability**

Europe