

Edgetek™ AT-000/000 HI 10 Natural

POM

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2070	MPa	ASTM D 638
Tensile Strength at Yield	48.3	MPa	ASTM D 638
Elongation at Break	38	%	ASTM D 638
Flexural Modulus	1640	MPa	ASTM D 790
Flexural Strength	58.9	MPa	ASTM D 790
Izod Impact notched, 1/8 in	96	J/m	ASTM D 256
Other properties			
Density	1380	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Melt temperature	188 - 210	°C	-

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

North America