

Epimax® POM-609

POM

Osterman's Engineered Polymers Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.02	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	60.8	MPa	ASTM D 638
Flexural Modulus	2551	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1410	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Regional Availability

North America

Features

Copolymer