

FV3035

POM

Cheng Yu Plastic Company Ltd.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|---------------|-------------|----------------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.0175 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 61 | MPa | ASTM D 638 |
| Flexural Strength | 92 | MPa | ASTM D 790 |
| Rockwell Hardness | M 80 | - | ASTM D 785 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.5 | mm | - |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1410 | kg/m ³ | ASTM D 792 |

Characteristics**Special Characteristics**
High impact or impact modified**Regional Availability**
Asia Pacific