

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>39</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	<b>1.9</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>1.8</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	<b>1200</b>	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	<b>0.19</b>	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	<b>2060</b>	J/(kg K)	-
<sup>[C]</sup> Ejection temperature	<b>140</b>	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>3000</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>65</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>7</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>15</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>150</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>150</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>166</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>106</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>110</b>	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>4</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>4</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>30</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>50</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>1E12</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>1E14</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>35</b>	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.65</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1410</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

U.V. stabilized or stable to weather

**Delivery form**

Pellets

**Features**

Copolymer

**Additives**

Release agent