

HOSTAFORM® LW15EWX

POM

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	2.5	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2650	MPa	ISO 527
^[C] Yield stress	63	MPa	ISO 527
^[C] Yield strain	19	%	ISO 527
^[C] Nominal strain at break	32	%	ISO 527
^[C] Charpy notched impact strength, +23°C	14	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	173	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	93	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1400	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Pellets

Regional Availability

North America, Europe

Additives

Lubricants, Release agent