

**HOSTAFORM® LX90**

POM

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>8</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2700</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>56</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>10</b>	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>4</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>166</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>88</b>	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.75</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1430</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding, Profile Extrusion

**Delivery form**

Pellets

**Additives**

Release agent

**Special Characteristics**

Light stabilized or stable to light, U.V. stabilized or stable to weather

**Features**

Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa