

HOSTAFORM® MT®24F01

POM

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	21	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Yield stress	58	MPa	ISO 527
^[C] Yield strain	8	%	ISO 527
^[C] Nominal strain at break	25	%	ISO 527
^[C] Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1440	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Additives

Lubricants, Release agent

Special Characteristics

Sterilizable, Ethylene Oxide (EtO) Sterilization, Steam sterilization

Features

Copolymer

Certifications

Food contact, Food approval BfR, Food approval FDA 21 CFR, Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved, Drug Master File, Device Master File

Applications

Medical

Regional Availability

North America, Europe, South and Central America, Near East/Africa