

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	1.4	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	1.7	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1450	MPa	ISO 527
^[C] Yield stress	33	MPa	ISO 527
^[C] Yield strain	7	%	ISO 527
^[C] Nominal strain at break	>50	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	18	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	68	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.6	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.6	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	40	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	60	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	1.2	%	Sim. to ISO 62
^[C] Humidity absorption	0.2	%	Sim. to ISO 62
^[C] Density	1260	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Light stabilized or stable to light

Features

Copolymer