

PC/ABS CB3110 anti static

(PC+ABS)

Wellman Advanced Materials

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	42	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	1900	MPa	ISO 178
Flexural strength	68	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, B	112	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Anti-static

Regional Availability

North America, Asia Pacific