

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	<b>1.1</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.1</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Stress at break	<b>60</b>	MPa	ISO 527
Strain at break	<b>11</b>	%	ISO 527
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>166</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>125</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	<b>1E16</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>1E14</b>	Ohm	IEC 62631-3-2
<b>Other properties</b>			
Density	<b>1590</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Processing**

Injection Molding

**Features**

Tribologic Grade

**Chemical Resistance**

General Chemical Resistance

**Applications**

Automotive, Sports Equipment

**Regional Availability**

Europe