

**KEBAFORM C 25 H**

POM

Barlog plastics GmbH

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>2.5</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>2.1</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>2.0</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2600</b>	MPa	ISO 527
Yield stress	<b>65</b>	MPa	ISO 527
Yield strain	<b>11</b>	%	ISO 527
Charpy impact strength, +23°C	<b>100</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>9</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>178</b>	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	<b>600</b>	-	IEC 60112
<b>Other properties</b>			
Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
Density	<b>1410</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Features**

High Crystallinity, Tribologic Grade, Copolymer

**Chemical Resistance**

General Chemical Resistance

**Applications**

Automotive, Sports Equipment

**Regional Availability**

Europe