

KEBAFORM C 270.0

POM

Barlog plastics GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	27	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	2.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2900	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Yield strain	7	%	ISO 527
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	110	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
Electrical properties			
ISO Data			
Volume resistivity	1E16	Ohm*m	IEC 62631-3-1
Surface resistivity	1E16	Ohm	IEC 62631-3-2
Other properties			
Humidity absorption	0.22	%	Sim. to ISO 62
Density	1410	kg/m ³	ISO 1183

Characteristics**Features**

Tribologic Grade, Copolymer

Chemical Resistance

General Chemical Resistance

Certifications

Food contact

Applications

Automotive

Regional Availability

Europe