

KEBAFORM C 906 XFA

POM

Barlog plastics GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	35	MPa	ISO 527
Yield strain	18	%	ISO 527
Nominal strain at break	70	%	ISO 527
Charpy impact strength, +23°C	100	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Other properties			
Density	1320	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

High impact or impact modified

Features

Low Emission, Tribologic Grade, Copolymer

Chemical Resistance

General Chemical Resistance

Applications

Automotive

Regional Availability

Europe