

PC/ABS Gebablend 95

(PC+ABS)

geba Kunststoffcompounds GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	21	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	5.5	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	30	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	115	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	133	°C	ISO 75-1/-2
Vicat softening temperature, B	136	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Applications

Automotive, Electrical and Electronical

Special Characteristics

High impact or impact modified

Regional Availability

Europe