

PC/ABS Gecomblend 3000 FR HT

(PC+ABS)

geba Kunststoffcompounds GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	240	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	30	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	120	°C	ISO 75-1/-2
Vicat softening temperature, B	120	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Applications

Automotive, Electrical and Electronical

Regional Availability

Europe