

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Tensile Strength	62	MPa	ISO 527
Yield strain	10	%	ISO 527
Strain at break	35	%	ISO 527
Flexural modulus, 23°C	2350	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5.5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	92	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	19	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1410	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	60 - 80	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	170 - 180	°C	-
Zone 2	170 - 180	°C	-
Zone 3	170 - 180	°C	-
Nozzle temperature	180 - 190	°C	-
Back pressure	2	MPa	-

Characteristics

Processing

Injection Molding

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific

Features

Low Emission