

PC-ABS V0

(PC+ABS)

MCPN Netherlands B.V.

Product Texts

Recommended temperature for heated bed is 100°C.

Mechanical properties**ISO Data**

	Value	Unit	Test Standard
Tensile Modulus	2400	MPa	ISO 527
Yield stress	65.1	MPa	ISO 527
Strain at break	62	%	ISO 527

Thermal properties**ISO Data**

	Value	Unit	Test Standard
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Other properties

	Value	Unit	Test Standard
Density	1180	kg/m ³	ISO 1183

Characteristics**Processing**

Additive Manufacturing

Delivery form

Monofilament

Special Characteristics

Flame retardant, Halogen-free

Features

Good Adhesion

Regional Availability

Europe