

POLIMID LUB C 100 Y10

POM

Poliblend S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3200	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at break	15	%	ISO 527
Izod notched impact strength, +23°C	5.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ISO 1183

Characteristics**Additives**

Lubricants

Regional Availability

Europe

Features

Copolymer