

POLIPOM C WR

POM

Poliblend S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2900	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	11	%	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	45	%	ISO 527
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	175	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
Other properties			
Density	1420	kg/m ³	ISO 1183

Characteristics**Features**

Copolymer

Regional Availability

Europe

Chemical Resistance

General Chemical Resistance