

Polyform C12

POM

Polyma Kunststoff GmbH & Co.KG

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2650	MPa	ISO 527
Tensile Strength	62	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	88	MPa	ISO 178
Charpy notched impact strength, +23°C	5.5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Other properties			
Density	1410	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Regional Availability

Europe