

LATAN 13 S/15

POM-GB

LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
Molding shrinkage, normal	2.1	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	8	%	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	15	%	ISO 527
Charpy impact strength, +23°C	20	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	110	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
Vicat softening temperature, B	150	°C	ISO 306
Coeff. of linear therm. expansion, parallel	80	E-6/K	ISO 11359-1/-2
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1480	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	180 - 210	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe