

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	80	MPa	ASTM D 638
Flexural Modulus	4500	MPa	ASTM D 790
Izod Impact notched, 1/8 in	50	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 264 psi	150	°C	ASTM D 648
Melting Temperature	170	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1480	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	170 - 210	°C	-
Mold temperature	60 - 90	°C	-

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Natural Color

Regional Availability

North America, Europe, South and Central America