

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|------------|-------------------|---------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.0055 | mm/mm | ASTM D 955 |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Modulus | 3447 | MPa | ASTM D 638 |
| Tensile Strength | 55.2 | MPa | ASTM D 638 |
| Flexural Modulus | 3447 | MPa | ASTM D 790 |
| Flexural Strength | 82.7 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 80.1 | J/m | ASTM D 256 |
| Electrical properties | | | |
| ASTM Data | | | |
| Surface Resistivity | 9.9E11 | Ohm | ASTM D 257 |
| Volume Resistivity | 9.9E10 | Ohm*cm | ASTM D 257 |
| Other properties | | | |
| Density | 1420 | kg/m ³ | ASTM D 792 |
| Moisture Content | 0.15 | % | - |
| Processing Recommendation Injection Molding | | | |
| Pre-drying - Temperature | 121 | °C | - |
| Pre-drying - Time | 2 | h | - |
| Melt temperature | 177 - 204 | °C | - |
| Mold temperature | 82.2 - 121 | °C | - |
| Injection pressure | 68.9 - 103 | MPa | - |

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Anti-static