

| Mechanical properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Modulus | 8300 | MPa | ISO 527 |
| Tensile Strength | 100 | MPa | ISO 527 |
| Strain at break | 2 | % | ISO 527 |
| Charpy impact strength, +23°C | 25 | kJ/m ² | ISO 179/1eU |

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 165 | °C | ISO 11357-1/-3 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1550 | kg/m ³ | ISO 1183 |

Characteristics

| Delivery form | Regional Availability |
|----------------------|------------------------------|
| Natural Color | Europe |

| Features |
|-----------------|
| Copolymer |