

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	12	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Melt flow index, MFI	15	g/10min	ISO 1133

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4300	MPa	ISO 527
Yield stress	54	MPa	ISO 527
Strain at break	10	%	ISO 527
Flexural modulus, 23°C	4100	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Strength	53	MPa	ASTM D 638
Elongation at Break	15	%	ASTM D 638
Flexural Modulus	3930	MPa	ASTM D 790
Flexural Strength	100	MPa	ASTM D 790
Rockwell Hardness	M 90	-	ASTM D 785
Taber Abrasion Resistance	23	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	33	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	118	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.7	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696
DTUL @ 66 psi	174	°C	ASTM D 648
DTUL @ 264 psi	152	°C	ASTM D 648

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1560	kg/m ³	ISO 1183
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1560	kg/m ³	ASTM D 792

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	190 - 210	°C	-
Mold temperature	60	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Features

Homopolymer

Delivery form

Pellets

Regional AvailabilityNorth America, Europe, Asia Pacific, South and Central America,
Near East/Africa