

Deniform 2510

POM-GF25

VAMP TECH SPA

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Izod impact strength, +23°C	26	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	7000	MPa	ASTM D 638
Tensile Strength at Yield	110	MPa	ASTM D 638
Elongation at Break	2.2	%	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	160	°C	ASTM D 648
Vicat Temperature	160	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1560	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70	°C	-
Pre-drying - Time	3	h	-
Melt temperature	190	°C	-
Mold temperature	90	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe