

**Iupital FG2025MZ**

POM-GF25

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	6.3	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	9800	MPa	ISO 527
Stress at break	135	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	8800	MPa	ISO 178
Flexural strength	200	MPa	ISO 178
Charpy impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	162	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	164	°C	ISO 75-1/-2
<b>Other properties</b>			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1590	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3 - 4	h	-
Mold temperature	60 - 100	°C	-
Zone 1	180	°C	-
Zone 2	190	°C	-
Zone 3	200	°C	-
Nozzle temperature	180 - 210	°C	-
Screw speed	80 - 120	rpm	-
Injection pressure	50 - 100	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Certifications**

Drinking water contact

**Applications**

Automotive, Electrical and Electronical, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa