

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10300	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	35	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1590	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific