

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	3.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	95	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	95	°C	ASTM D 3418
Other properties			
Density	895	kg/m ³	ISO 1183
Density	895	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Melt temperature	260	°C	-

Characteristics

Processing

Film Extrusion, Other Extrusion

Delivery form

Pellets

Additives

Antiblocking agent

Features

Heat Sealable

Certifications

Food contact, Food approval FDA 21 CFR, Food contact notification (FCN)

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa