

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 1.7 | g/10min | ISO 1133 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |
| ASTM Data | | | |
| Melt Flow Index, MFI | 1.7 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|-------|------|----------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 105 | °C | ISO 11357-1/-3 |
| ASTM Data | | | |
| Melting Temperature | 105 | °C | ASTM D 3418 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 913 | kg/m ³ | ISO 1183 |
| Density | 913 | kg/m ³ | ASTM D 792 |

| Processing Recommendation Extrusion | Value | Unit | Test Standard |
|-------------------------------------|-------|------|---------------|
| Melt temperature | 260 | °C | - |

Characteristics

Processing

Film Extrusion, Other Extrusion

Delivery form

Pellets

Additives

Antiblocking agent

Features

Heat Sealable

Certifications

Food contact, Food approval FDA 21 CFR, Food contact notification (FCN)

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa