

**Product Texts**

Modified ethylene acid terpolymer resin

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>32</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>32</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>107</b>	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	<b>107</b>	°C	ASTM D 3418
Vicat Temperature	<b>56</b>	°C	ASTM D 1525

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>940</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>940</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**  
Other Extrusion, Coating

**Delivery form**  
Pellets

**Features**  
Good Adhesion, Heat Sealable

**Certifications**  
Food contact, Food approval FDA 21 CFR

**Applications**  
Packaging

**Regional Availability**  
Asia Pacific