

**Product Texts**

Modified ethylene acid terpolymer resin

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	24	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	24	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	108	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	108	°C	ASTM D 3418
Vicat Temperature	64	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	930	kg/m <sup>3</sup>	ISO 1183
Density	930	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Other Extrusion, Coating

**Delivery form**

Pellets

**Features**

Good Adhesion, Heat Sealable

**Certifications**

Food contact, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

Asia Pacific