

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	26	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Melt flow index, MFI	30	g/10min	ISO 1133

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2700	MPa	ISO 527
Yield stress	62	MPa	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
<sup>[C]</sup> Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA

**ASTM Data**

Tensile Strength	60	MPa	ASTM D 638
Elongation at Break	20	%	ASTM D 638
Flexural Modulus	2800	MPa	ASTM D 790
Flexural Strength	91	MPa	ASTM D 790
Izod Impact notched, 1/8 in	35	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	157	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

**ASTM Data**

UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	100	E-6/K	ASTM D 696
DTUL @ 66 psi	157	°C	ASTM D 648
DTUL @ 264 psi	100	°C	ASTM D 648

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1390	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1390	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	180 - 210	°C	-
Mold temperature	60	°C	-

**Characteristics****Processing**

Injection Molding

**Features**

Tribologic Grade, Copolymer

**Delivery form**

Pellets

**Additives**

Lubricants

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa