

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	26	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Melt flow index, MFI	30	g/10min	ISO 1133

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2900	MPa	ISO 527
Yield stress	67	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2750	MPa	ISO 178
<sup>[C]</sup> Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA
<b>ASTM Data</b>			
Tensile Strength	66	MPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Modulus	2800	MPa	ASTM D 790
Flexural Strength	93	MPa	ASTM D 790
Rockwell Hardness	M 88	-	ASTM D 785
Izod Impact notched, 1/8 in	69	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	103	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	159	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Coefficient of Thermal Expansion, MD	100	E-6/K	ASTM D 696
DTUL @ 66 psi	163	°C	ASTM D 648
DTUL @ 264 psi	124	°C	ASTM D 648

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1410	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1410	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	180 - 210	°C	-
Mold temperature	60	°C	-

## Characteristics

### Processing

Injection Molding

### Features

Copolymer

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa