

Titacon EX910

POM

Titan Plastics Compounds Co., Ltd.

| Mechanical properties | Value | Unit | Test Standard |
|---------------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 45 | MPa | ISO 527 |
| Flexural modulus, 23°C | 1750 | MPa | ISO 178 |
| Flexural strength | 70 | MPa | ISO 178 |
| Charpy notched impact strength, +23°C | 5 | kJ/m ² | ISO 179/1eA |

| Thermal properties | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 95 | °C | ISO 75-1/-2 |
| Burning behav. at thickness h | HB | class | IEC 60695-11-10 |

| Electrical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Volume resistivity | 1000 | Ohm*m | IEC 62631-3-1 |
| Surface resistivity | 1E8 | Ohm | IEC 62631-3-2 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1480 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 100 | °C | - |
| Pre-drying - Time | 3 | h | - |
| Melt temperature | 170 - 200 | °C | - |
| Mold temperature | 60 - 100 | °C | - |

Characteristics**Processing**

Injection Molding

Special Characteristics

Anti-static

Delivery form

Black, Natural Color

Regional Availability

Asia Pacific