

Titacon NW901

POM

Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	52	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	73	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1360	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	170 - 200	°C	-
Mold temperature	60 - 100	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Additives

Lubricants

Features

Tribologic Grade

Regional Availability

Asia Pacific