

Witcom POM-C-EC-E-ST

POM

Wittenburg B.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	43	MPa	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Flexural strength	43	MPa	ISO 178
Izod impact strength, +23°C	125	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	11	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	105	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Electrical properties			
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Other properties			
Water absorption	0.8	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1400	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.05	%	-
Melt temperature	170 - 210	°C	-
Mold temperature	50 - 120	°C	-
Back pressure	0 - 0.5	MPa	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Copolymer

Special Characteristics

Increased electrical conductivity, High impact or impact modified

Regional Availability

Europe