

RamOfin PPC311J4BK11

PP-(GF+GB)20

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Other Standards^[S]			
Molding shrinkage, parallel	0.5	%	Producer Method
Molding shrinkage, normal	0.8	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Tensile Strength	40	MPa	ISO 527
Strain at break	4.3	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Flexural strength	65	MPa	ISO 178
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.1	%	-
Mold temperature	30 - 70	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 250	°C	-

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa