

**RamLloy PBB1007BK10-33**

(PC+ABS)

Polyram

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>18</b>	g/10min	ISO 1133
Temperature	<b>260</b>	°C	-
Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0.6</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2230</b>	MPa	ISO 527
Tensile Strength	<b>50</b>	MPa	ISO 527
Yield strain	<b>4.2</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>42</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>610</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>90</b>	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	<b>1130</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Mold temperature	<b>50 - 90</b>	°C	-
Feed temperature	<b>60 - 70</b>	°C	-
Zone 1	<b>230 - 240</b>	°C	-
Zone 2	<b>230 - 240</b>	°C	-
Zone 3	<b>240 - 265</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Certifications**

RoHS compliant

**Delivery form**

Black

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa