

**RamOfin PPH306S6BK10**

PP-GB30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>8</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>1850</b>	MPa	ISO 527
Tensile Strength	<b>26</b>	MPa	ISO 527
Strain at break	<b>15</b>	%	ISO 527
Flexural modulus, 23°C	<b>1800</b>	MPa	ISO 178
Flexural strength	<b>43</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>24</b>	kJ/m <sup>2</sup>	ISO 179/1eU

Other properties	Value	Unit	Test Standard
Density	<b>1120</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.1</b>	%	-
Mold temperature	<b>30 - 70</b>	°C	-
Feed temperature	<b>60 - 70</b>	°C	-
Zone 1	<b>200 - 230</b>	°C	-
Zone 2	<b>200 - 230</b>	°C	-
Zone 3	<b>200 - 250</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Features**

Homopolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa