

TAIRILOY® AC2190

(PC+ABS)

Formosa Chemicals & Fibre Corp.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	240	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
Temperature	240	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Strength	66	MPa	ISO 527
Flexural modulus, 23°C	2060	MPa	ISO 178
Flexural strength	88	MPa	ISO 178
Rockwell hardness	R 119	-	ISO 2039-2
ASTM Data			
Tensile Strength	66	MPa	ASTM D 638
Flexural Modulus	2060	MPa	ASTM D 790
Flexural Strength	88.3	MPa	ASTM D 790
Rockwell Hardness	R 119	-	ASTM D 785
Izod Impact notched, 1/8 in	804	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	126	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	126	°C	ASTM D 648
Other properties			
Value			
Density	1140	kg/m ³	ISO 1183
Density	1140	kg/m ³	ASTM D 792
Processing Recommendation Extrusion			
Value			
Pre-drying - Temperature	100 - 110	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	200 - 260	°C	-
Nozzle temperature	210 - 260	°C	-

Characteristics**Processing**

Other Extrusion

Certifications

RoHS compliant

Special Characteristics

High impact or impact modified

Regional Availability

Asia Pacific