

OMNIPRO® HPP GRC20

PP-GF20

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5200	MPa	ISO 527
^[C] Stress at break	74	MPa	ISO 527
^[C] Strain at break	3.4	%	ISO 527
^[C] Charpy impact strength, +23°C	9.5	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1040	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, South and Central America